

Fiberglass surface tissue

PRODUCT DESCRIPTION

Fiberglass surface tissue is mainly used for inner and outer surface treatment of FRP products, to make the surface smooth and even. It is suitable for saturated polyester resin, epoxy resin and phenolic resin. According to the applying process, it can be divided into winding ST (W) series, hand lay-up ST (H) series and pultrusion ST (P) series.



CHARACTERISTICS

- ◆ Fiber Uniformly Dispersed
- ◆ Smooth and Soft Surface
- ◆ Fast Wet-out
- ◆ Excellent Molding Property

TECHNICAL DATA

Product code	Unit Weight	LOI	MD Tensile Strength	Moisture Content	Penetrating time
	g/m ²	%	N/5CM	%	S
F-BM-30H	30	≤10	≥25	≤0.5	≤10 (Two layers)
F-BM-50H	50	≤10	≥40	≤0.5	≤15 (Two layers)
F-BM-30W	30	≤10	≥30	≤0.5	≤10 (Two layers)
F-BM-50W	50	≤10	≥50	≤0.5	≤15 (Two layers)
F-BM-100W	100	≤10	≥180	≤0.5	≤15 (One layer)
F-BM-60P	60	≤20	≥100	≤0.5	—
F-BM-90P	90	≤15	≥120	≤0.5	—
F-BM-100P	100	≤15	≥180	≤0.5	—
Testing Basis	ISO3374	ISO 1887	ISO3342	ISO 3344	EN 14118
Paper core diameter: 76/152mm					

Remark: 1. Other specification can be customized according to customer' s demand.

2. The technical data above is for reference only

PACKING

Every roll in plastic film without pallet.

STORAGE

This product should be stored in a dry, ventilated and rainproof place, with temperatures from 5°C to 35°C and humidity between 35% and 65%. It is recommended to be kept in intact package when not used to avoid damp.

Version #: No.201911

Address: No.20 Jiangjun Ave., Nanjing, P.R. China

URL: www.fiberglassnonwoven.com

E-mail: sales@njefg.com

Tel.: 0086 25 52270147 / 58321911

Fax: 0086 25 58321442

WhatsApp: 0086 18851651909